

CRESTOMER 1153PA

Long Open Time Structural Adhesive

Introduction

Crestomer 1153PA is a two part pre-accelerated, highly thixotropic structural adhesive based on unsaturated urethane-acrylate in styrene monomer. It has a long open time of 90 minutes. It is used in many structural composite applications and has excellent adhesion to FRP laminates, core materials, wood and metals. Due to its excellent adhesion to a wide range of materials, Crestomer 1153PA can also be used as a general purpose adhesive. It is also used to contour joints in FRP components, to build up damaged areas and can be used to bond "green" FRP.

Characteristics using 2 % Butanox M50 Catalyst

Characteristics	Typical Value	Unit
Working Time/Geltime ¹	90	Minutes
Fixture Time ²	8.5	Hours
Gap Filling	1 - 15	mm
Flash Point	33	°C
Colour Change (over cure)	None	-

Physical Data – Uncured

Property	Value	Unit
Viscosity ³	250,000 – 320,000	cP
Specific Gravity	1.0 – 1.1	-
Volatile Content	47	%
Mix Ratio ⁴	50:1	Volume
Colour/Appearance	Purple/Brown Gel	-
Stability at 20°C ⁵	3	Months

Physical Data – Cured

Property	Typical Value	Unit	Test Method
Hardness	65	Shore D	BS EN ISO 868:2003
Maximum Tensile Strength	26	MPa	BS EN ISO 527-2:1996
Tensile Modulus	1,350 – 1,450	MPa	BS EN ISO 527-2:1996
Elongation at Break	100	%	BS EN ISO 527-2:1996
Water Absorption	0.36	%	BS EN ISO 62:1999

Bond Joint Strength – Typical Lap Shear Strengths (MPa) BS ISO 4587:2003⁶

	FRP	Marine Ply	Aluminium	Stainless Steel	Teak
FRP	10*	-	-	-	-
Marine Ply	-	5*	-	-	-
Aluminium	-	-	15	-	-
Stainless Steel	-	-	-	12	-
Teak					5*

Values are based on substrate failure where marked by *

Surface Preparation

Crestomer 1153PA has excellent adhesion to FRP material provided that the surface has been maintained free of dust and grease. This can be guaranteed by the use of proprietary strippable cloths such as peel ply (without lubricant contaminants). If the laminate surfaces are more than 3 days old, it is recommended that they are lightly abraded. They should then be wiped with acetone or styrene on a lint-free, clean cloth prior to bonding.

Application

Crestomer 1153PA is supplied pre-accelerated. The required hardener is Butanox M50 (or equivalent MEKP catalyst). The catalyst is added at 2% w/v. Crestomer 1153PA can be applied with a spatula or from a dispensing unit, taking care to keep air entrapment to a minimum. The maximum dimensions recommended are gap height 15 mm and joint width 40 mm. Bulk volumes of Crestomer 1153PA may lead to unsatisfactory cure and reduced mechanical performance. Application should always be carried out at temperatures above 15 °C. Recommended temperature range for application is 18 and 25 °C.

Storage

Crestomer 1153PA should be stored in its original container and out of direct sunlight. It is recommended that the storage temperature should be between 15 and 20 °C. Ideally, containers should be opened only immediately prior to use. Products should never be frozen.

Packaging

Crestomer 1153PA is supplied in 25 kg and 200 kg containers.

Health and Safety

See separate Material Safety Data Sheet.

Notes

1. Geltime measured with 100g mass of adhesive at 25 °C.
2. Time taken at 23 °C (ambient temperature) to achieve 1.4MPa strength in lap-shear tests according to BS ISO 4587:2003⁶.
3. Measured using Brookfield Viscometer at 25 °C.
4. Mix ratio based on volume and weight for both machine dispensing and hand mixing.
5. Stability defined from date of dispatch when left un-opened in the original containers and stored out of direct sunlight.
6. Surface preparation methods vary between substrates; FRP – removal of strippable cloth; Marine-ply – dust-free and degrease; Aluminium – P2 etch; Steel –degrease, abrade and degrease.

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage handling and application of these materials, Scott Bader cannot accept liability for results obtained

Version 2: October 2013

All information on this data sheet is based on laboratory testing and is not intended for design purposes. Scott Bader makes no representations or warranties of any kind concerning this data. Due to variance of storage, handling and application of these materials, Scott Bader cannot accept liability for results obtained. The manufacture of materials is the subject of granted patents and patent applications; freedom to operate patented processes is not implied by this publication.

SCOTT BADER COMPANY LIMITED

Wollaston, Wellingborough, Northamptonshire, NN29 7RL

Telephone: +44 (0) 1933 663100

Facsimile: +44 (0) 1933 666623

www.scottbader.com