

## TYPE APPROVAL CERTIFICATE

Certificate No:  
**TAK000007R**  
Revision No:  
**1**

**This is to certify:****That the Glass Fibre Products**

with type designation(s)

**Quadri-axial: (0°/±45°/90°) (625-3090 g/m<sup>2</sup>) with and without chopped strand mats (100-500 g/m<sup>2</sup>)**

Issued to

**Telateks Tekstil Urunleri Sanayi Ve Ticaret A.S.  
(METYX Composites)  
Tuzla, Istanbul, Turkey**

is found to comply with

**DNV GL rules for classification – High speed and light craft  
DNV GL class programme DNVGL-CP-0467 – Type approval – Uni- and multi-axial multi-ply fabrics made of glass fibres  
Det Norske Veritas Standards' for Certification No. 2.21, Craft, 2010  
Det Norske Veritas' Standards for Certification No. 2.20, Lifeboats and Rescue Boats, 2007**

**Application :**

**For use in marine vessels according to stated Rules/Standards.**

**Product(s) approved by this certificate is/are accepted for installation on all vessels classed by DNV GL.**

Issued at **Høvik** on **2021-01-21**

for **DNV GL**

This Certificate is valid until **2026-01-20**.

DNV GL local station: **Istanbul**

Approval Engineer: **Gisle Hersvik**

**Gustav Heiberg  
Head of Section**

This Certificate is subject to terms and conditions overleaf. Any significant change in design or construction may render this Certificate invalid. The validity date relates to the Type Approval Certificate and not to the approval of equipment/systems installed.

LEGAL DISCLAIMER: Unless otherwise stated in the applicable contract with the holder of this document, or following from mandatory law, the liability of DNV GL AS, its parent companies and subsidiaries as well as their officers, directors and employees ("DNV GL") arising from or in connection with the services rendered for the purpose of the issuance of this document or reliance thereon, whether in contract or in tort (including negligence), shall be limited to direct losses and under any circumstance be limited to 300,000 USD.



Job Id: **262.1-011606-11**  
Certificate No: **TAK000007R**  
Revision No: **1**

## Product description

### METYX® Glass Fibre Reinforcements:

Quadri-axial: (Q) (0°/±45°/90°) (625-3090 g/m<sup>2</sup>) with and without (M) (100-500 g/m<sup>2</sup>)

The following properties have been verified by Type Testing of laminates:

| Property - Orientation            | Test Method  | Q 625  | Q 940  |      |     |
|-----------------------------------|--|--------|--------|------|-----|
| Tensile Strength - 0°             | ISO 527  | 208    | 201    | msmv | MPa |
| Tensile Modulus - 0°              | ISO 527  | 14 489 | 14 724 | msv  | MPa |
| Tensile Elongation - 0°           | ISO 527  | 3.0    | 2.3    | msmv | %   |
|                                   |  |        |        |      |     |
| Glass content                     | ISO 1172   | 50.2   | 52.9   | mean | %   |
|                                   |  |        |        |      |     |
| Flexural Strength - 0°            | ISO 14125  | 410    | 330    | msmv | MPa |
| Flexural Modulus - 0°             | ISO 14125  | 13 371 | 14 871 | msv  | MPa |
| Flexural Elongation - 0°          | ISO 14125  | 4.2    | 3.8    | msmv | %   |
|                                   |  |        |        |      |     |
| Glass content                     | ISO 1172   | 50.0   | 53.3   | mean | %   |
| Resin                             | CE 266 N12 ISO Polyester                             |        |        |      |     |
| Curing Procedure for Type Testing | 24 hrs at room temperature, post-cured 3 hrs at 80°C |        |        |      |     |

#### Legends:

*msmv* = Manufacturer's Specified Minimum Value, verified to be below mean - 2 x standard deviation of Type Test results

*msv* = Manufacturer's Specified Value, verified to be within ± 10% of mean of Type Test results.

*mean* = Mean of Type Test results

Q: 0/90/+45/-45 Quadri-axial

M: Chopped Strand Mat

## Application/Limitation

Manufacture of FRP components for applications including marine vessels - and rotor blades within wind energy (ref. DNVGL-ST-0376).

The approval covers the weight ranges stated above.

Any significant changes in design and / or quality of the material will render the approval invalid.

## Type Approval documentation

1. Assessment Report from DNV GL Istanbul of 2020-12-17.
2. Assessment Report from DNV GL Istanbul of 2015-12-09.
3. Application for Type Approval of 2015-11-24.
4. Survey Report from DNV Istanbul of 2011-04-15.
5. Email from DNV Istanbul of 2006-01-16, incl. email from Metyx – Telateks A.S. of 2006-01-09, general type approval information, pictures and mechanical test results.
6. Email from Metyx – Telateks S.A. of 2005-10-28, incl. Technical Data Sheets.

Job Id: **262.1-011606-11**  
Certificate No: **TAK000007R**  
Revision No: **1**

## Tests carried out

Type Testing carried out in accordance with **Type Approval documentation.**

## Marking of product

Product shall be marked with *manufacturer's name*: **Telateks Tekstil Urunleri San. ve A.S. (Metyx®), Tuzla / Istanbul, Turkey** and *type designation*.

The marking is to be carried out in such a way that it is visible, legible and indelible. The marking of product is to enable traceability to the DNV GL Type Approval Certificate.

## Periodical assessment

The scope of the Periodical Assessment is to verify that the conditions stipulated for the Type Approval is complied with and that no alterations are made to the product design or choice of materials.

Periodical assessments (for Certificate Retention and Certificate Renewal) shall be performed according to DNVGL-CP-0338.

This certificate is only valid if required Periodical assessments are carried out with satisfactory results. To check the validity of this certificate, please look it up in <https://approvalfinder.dnvgl.com>

END OF CERTIFICATE