

TYPE APPROVAL CERTIFICATE

This is to certify:

That the **Carbon Fibre Products**

with type designation(s)

Tri-axial: (0°/+45°/-45°) (200-2000 g/m²) with or without chopped strand mats (50-500 g/m²)

Issued to

**Telateks Tekstil Urunleri Sanayi Ve Ticaret A.S.
(METYX Composites)
Tuzla, Istanbul, Türkiye**

is found to comply with

DNV class programme DNV-CP-0434 – Type approval – Uni- and multi-axial multi-ply fabrics made of carbon fibres

DNV rules for classification – High speed and light craft

DNV standard DNV-ST-0342 – Craft

Application :

For use in marine vessels according to stated Rules/Standards.

Product(s) approved by this certificate is/are accepted for installation on all vessels classed by DNV.

Issued at **Hamburg** on **2023-04-04**

This Certificate is valid until **2028-04-03**.

DNV local unit: **Istanbul**

Approval Engineer: **Gisle Hersvik**

for **DNV**

Thorsten Lohmann
Head of Section

This Certificate is subject to terms and conditions overleaf. Any significant change in design or construction may render this Certificate invalid. The validity date relates to the Type Approval Certificate and not to the approval of equipment/systems installed.

LEGAL DISCLAIMER: Unless otherwise stated in the applicable contract with the holder of this document, or following from mandatory law, the liability of DNV AS, its parent companies and their subsidiaries as well as their officers, directors and employees ("DNV") arising from or in connection with the services rendered for the purpose of the issuance of this document or reliance thereon, whether in contract or in tort (including negligence), shall be limited to direct losses and under any circumstance be limited to 300,000 USD.



Product description

METYX® Carbon Fibre Reinforcements

Tri-axial Carbon Fibre products of 0°/±45° orientations:

(CXL) (0°/±45°) (200-2000 g/m²) with and without CSM (50-500 g/m²)

Legends:

C: Carbon
 CSM: Chopped Strand Mat
 L: Longitudinal (0°)
 X: Double-bias (+45°/-45°)

The following properties have been verified by Type Testing of laminates:

Property – Orientation	Test Method	CXL800		
Tensile Strength - 0°	ISO 527-4	640	mean	MPa
Tensile Modulus - 0°	ISO 527-4	47,4	msv	GPa
Fibre volume content	EN 2564	53.6	mean	%
Compressive Strength - 0°	ISO 14126	605	mean	MPa
Compressive Modulus - 0°	ISO 14126	67.4	msv	GPa
Fibre volume content	EN 2564	53.4	mean	%
Flexural Strength - 0°	ISO 14125	929	mean	MPa
Fibre volume content	EN 2564	53.6	mean	%
Resin	Epoxy System: Baxxores ER5300/Baxxodur EC5310			
Curing Procedure for Type Testing	Post-cured 12 hrs at 80°C			

Legends:

msv = Manufacturer's Specified Value, verified to be within ± 10% of mean of Type Test results.
mean = Mean of Type Test results

Application/Limitation

The approval covers the weight ranges stated above.

Any significant changes in design and / or quality of the material will render the approval invalid.

Type Approval documentation

Tests carried out

Type Testing carried out according to **Type Approval documentation**.

Marking of product

Product shall be marked with *manufacturer's name*: **Telateks Tekstil Urunleri Sanayi Ve Ticaret A.S. (METYX Composites)**, **Tuzla / Istanbul, Turkey** and *type designation*.

The marking is to be carried out in such a way that it is visible, legible and indelible. The marking of product is to enable traceability to the DNV Type Approval Certificate.

Periodical assessment

The scope of the Periodical Assessment is to verify that the conditions stipulated for the Type Approval is complied with and that no alterations are made to the product design or choice of materials.

Periodical assessments (for Certificate Retention / Certificate Renewal) shall be performed according to DNV-CP-0338.

This certificate is only valid if required Periodical assessments are carried out with satisfactory results. To check the validity of this certificate, please look it up in <https://approvalfinder.dnv.com>



Job Id: **262.1-039402-1**
Certificate No: **TAK000027N**

END OF CERTIFICATE