

A2000 Release film



Tel: +44 (0) 1274 550500
Fax: +44 (0) 1274 550501
Email: sales@aerovac.com
Website: www.aerovac.com

- Inexpensive release film, mainly used during the processing of flat or simple curvature components for de-bulk or out of autoclave cure conditions.
- Exhibits excellent release characteristics from all commonly used resin systems.
- Ideal for use in resin infusion applications.

PHYSICAL PROPERTIES

- Maximum use temperature 150°C
- Colour Red
- Standard perforations P3, P6, P31
- Tensile strength (at break) 35MPa
- Elongation (at break) 500%
- Density 0.900g/cm³

AVAILABILITY & PACKAGING

- Thicknesses 30μ, 50μ
- Standard width 1.52m
- Standard length 400m
- Internal core size 76mm

STORAGE & HANDLING

- Store in original packaging.
- Handling of these products must conform to individual company guidelines and health and safety regulations.

Aerovac Systems Ltd www.aerovac.com	Aerovac Systems Italy S.r.l www.aerovac.it	Aerovac Systèmes France www.aerovac.fr	Richmond Aircraft Products www.richmondaircraft.com
-----------------------------------------------------------------------------	-----------------------------------------------------------------------------------	-------------------------------------------------------------------------------	------------------------------------------------------------------------------------------------------

Aerovac Systems Ltd.

All statements, technical information and recommendations contained in this publication are based on tests believed to be reliable, but their accuracy and/or completeness are not guaranteed. The user shall determine the suitability for this particular purpose and shall assume all risk and liability in connection herewith. All values stated are nominal. For further details about tolerances please contact Aerovac Systems quality department.

Revised: February 2010